

**DESIGN AND CONSTRUCTION OF SMART MATERIALS BASED ON
PIEZORESISTIVE SENSORS AND MULTILAYER ACTUATORS**

FINAL PROGRESS REPORT

WALTER A. SCHULZE and WILLIAM B. CARLSON

April 26, 1996

U.S. Army Research Office

Grant Number **DAAL03-92-G-0374**

**NEW YORK STATE COLLEGE OF CERAMICS
at ALFRED UNIVERSITY, ALFRED, NEW YORK**

19960528 113

Approved for Public Release;
Distribution Unlimited

The views, opinions, and/or findings contained in this report are those of the authors and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

PTCR (positive temperature coefficient of resistance) barium titanate was the active material for a ceramic sensor which employed piezoresistivity to detect changes in applied stress. High purity, chemically prepared barium titanate was donor-doped at an optimum level of 0.30 at% lanthanum to provide semiconductivity. A transition metal counterdopant was added at a level of less than 0.10 at% in some cases, to enhance the PTCR effect. The donor dopant and counterdopant were added to the powder through a special precipitation technique. Tape-cast sheets of undoped and PTCR BaTiO_3 were laminated to produce a three-layer "trilaminate" - a sintered structure which has two semiconducting PTCR layers separated by an insulating layer. The trilaminate was exposed to mechanical stress in a four-point bend configuration (placing one semiconducting layer completely in tension, the other in compression), and the resistivities for both stress states were measured concurrently as functions of applied stress and temperature.

Piezoresistivity was found to be extremely sensitive to temperature, reaching a peak just above the Curie temperature, T_C . The piezoresistive effect, which was positive in compression and negative under tensile stress, was dependent on the presence of a well-formed grain boundary potential barrier, but the species of counterdopant had little impact. Formation of $(\text{Ba},\text{Sr})\text{TiO}_3$ solid solutions shifted the peak to lower temperatures (corresponding to the T_C shift), and reduced its magnitude. Broadening of the piezoresistivity peak is observed as the thickness of the semiconducting layers of the trilaminate decreases.

The results were in semi-quantitative agreement with a potential barrier model for PTCR BaTiO_3 . This model is based on the Heywang model of the grain boundary as a back-to-back Schottkey barrier, in combination with Devonshire's thermodynamic phenomenology which describes polarization in terms of electric field, mechanical stress, and temperature. Original modifications to this combined model account for the non-linear electric field dependence of polarization in the vicinity of the grain boundary, and the circular dependence of field, polarization, and potential barrier height.

A smart material package consisting of piezoresistive sensors and a piezoelectric actuator has been proposed. The proposed device has the advantage of requiring only a simple resistor network as a control circuit and a DC voltage source. The piezoresistive sensor will allow a mechanical stress to control the response of the actuator by controlling the amount of power let through.

The responses of such a smart material package were analyzed using finite element methods. Results of simplified analyses were compared to closed form solutions in order to determine the degree of accuracy of the more complex models. Static and dynamic responses of the package were simulated over a wide range of pressures. Results of the finite element analysis of the piezoelectric effect matched the results of the closed form solutions within 1 %. The enhanced compliant nature of the device was demonstrated under both static and dynamic pressures. The developed algorithms can be used for analysis of packages having different geometries or containing different materials.

The piezoresistive sensor proposed for use in this smart package is an 0-3 ceramic/polymer composite. Such a material has been shown to have order of magnitude decreases in resistivity with applied pressures. A range of polymer systems having varying flexibilities have been investigated for the insulating polymeric matrix. The use of carbon and Fe_3O_4 particles have been investigated for use as the filler material. The amount of filler in the composites has been studied to determine the optimum solids loading. The different choices of filler and polymer have been investigated to determine which combination would yield the composites with the most pronounced changes in resistivity, as well as have increased reproducibility. Also, work has been done to minimize the volume of the sensor with respect to the volume of the entire smart package. The actuator for the proposed package consists of a commercially available PZT stack.

LIST OF PUBLICATIONS

J.S. Capurso, "Aspects of Piezoresistivity in Semiconducting Barium Titanate Ceramics," Ph.D. Thesis, New York State College of Ceramics at Alfred University, Alfred, New York, April, 1996.

J.S. Capurso and W.A. Schulze, "Piezoresistivity in PTCR Barium Titanate Ceramics: I, Experimental Findings," submitted for publication in *J. Am. Ceram. Soc.*

J.S. Capurso and W.A. Schulze, "Piezoresistivity in PTCR Barium Titanate Ceramics: II, Mathematical Modeling," submitted for publication in *J. Am. Ceram. Soc.*

W.A. Schulze and J.S. Capurso, "Ceramic Piezoresistive Sensors," to be published in *The ISHM Journal of Microcircuits & Electronic Packaging*

J.M. Frommelt, "Finite Element Analysis of a Piezoresistive-Piezoelectric Smart Material Package," M.S. Thesis, New York State College of Ceramics at Alfred University, Alfred, New York, January, 1995.

J.S. Capurso, A.B. Alles, and W.A. Schulze, "Processing of Laminated Barium Titanate Structures for Stress-Sensing Applications," *J. Am. Ceram. Soc.*, **78** [9] 2476-80 (1995).

J. M. Frommelt, S. M. Pilgrim, W. B. Carlson, and W. A. Schulze, "Modeling of Piezoresistively-Controlled Electromechanical Smart Material," *J. Intell. Mater. Systems Structures*, **6** [5] 684 -90(1995).

J.S. Capurso and W.A. Schulze, "A Stress-Sensing Ceramic Device Based on PTCR Barium Titanate," *Proc. IEEE Intl. Symp. Appl. Ferroelectrics*, 9th (1994) 731-34.

W. B. Carlson, S. M. Pilgrim, W. A. Schulze, Y. S. Kato, and J. M. Frommelt, "Flexi-Distortional Piezoelectric Sensor Results," *Proc. IEEE Intl. Symp. Appl. Ferroelectrics*, 9th (1994) 770-71.

J.S. Capurso, A.B. Alles, and W.A. Schulze, "Piezoresistive Ceramic Sensor Based on Barium Titanate," pp. 393-400 in *Ceramic Transactions, vol. 43: Ferroic Materials: Design, Preparation, and Characteristics*, A.S. Bhalla, K.M. Nair, I.K. Lloyd, H. Yanagida, and D.A. Payne, eds., American Ceramic Society, Westerville, OH, 1994.

REPORT OF INVENTION

U.S. Patent Number 5,225,126: Piezoresistive Sensor; A.B. Alles and W.A. Schulze, Alfred University, Alfred, New York, July 6, 1993.

LIST OF PARTICIPATING SCIENTIFIC PERSONNEL

Dr. Walter A. Schulze - principal investigator
Dr. William B. Carlson - principal investigator

Joseph S. Capurso - research assistant (earned Ph.D., Ceramics in 1996)
Jon M. Frommelt - research assistant (earned M.S., Ceramic Engineering in 1995)
Paul C. Huber - research assistant
Carl J. Carney - research assistant

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE 26 Apr 1996	3. REPORT TYPE AND DATES COVERED Final 1 Sep 92 - 29 Feb 96		
4. TITLE AND SUBTITLE Design And Construction Of Smart Materials Based On Piezoresistive Sensors And Multilayer Actuators		5. FUNDING NUMBERS DAAL03-92-G-0374		
6. AUTHOR(S) W.A. Schulze and W.B. Carlson		7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) New York State College of Ceramics at Alfred University Alfred, New York 14802		
8. PERFORMING ORGANIZATION REPORT NUMBER		9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211		
10. SPONSORING / MONITORING AGENCY REPORT NUMBER ARO 28745-9-MS-SM		11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.		
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.		12b. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words) PTCR (positive temperature coefficient of resistance) barium titanate was the active material for a ceramic sensor which employed piezoresistivity to detect changes in applied stress. Tape-cast sheets of undoped and PTCR BaTiO ₃ were laminated to produce a three-layer "trilaminate" - a sintered structure which has two semiconducting PTCR layers separated by an insulating layer. The trilaminate was exposed to mechanical stress in four-point bend (placing one semiconducting layer completely in tension, the other in compression), and the resistivities for both stress states were measured concurrently as functions of applied stress and temperature. The results were in semi-quantitative agreement with a modified potential barrier model for PTCR BaTiO ₃ , based on the Heywang model and Devonshire's thermodynamic phenomenology. Original modifications to this combined model account for non-linear polarization and the interdependence of field, polarization, and barrier height. A smart material package consisting of piezoresistive sensors and a piezoelectric actuator has been proposed, having the advantage of requiring only a simple resistor network as a control circuit and a DC voltage source. The piezoresistive sensor will allow a mechanical stress to control the response of the actuator by controlling the amount of power let through. The piezoresistive sensor proposed for use in this smart package is an 0-3 ceramic/polymer composite. A range of polymer systems having varying flexibilities have been investigated for the insulating polymeric matrix.				
14. SUBJECT TERMS Piezoresistivity, PTCR, barium titanate, composites, smart materials		15. NUMBER OF PAGES 6		
16. PRICE CODE		17. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED		
18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED		19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED		20. LIMITATION OF ABSTRACT UL